



UEWF U2 Enamelled Round Copper Wire Heat Resistant 0.04mm - 1.60mm UL Approved

Our Product Introduction

Basic Information

- Place of Origin: China
- Brand Name: PEWSC
- Certification: UL
- Model Number: 0.04mm-1.60mm
- Minimum Order Quantity: The MOQ varies according to the size of the specification
- Price: Copper price plus processing fee plus freight
- Packaging Details: Box
- Delivery Time: 3-5 work days
- Payment Terms: T/T 100% payment before shipment
- Supply Ability: Delivery 10-15 days after next order



Product Specification

- Product Type: UEWF U2
- Voltage Rating: 2800V
- Specification: 0.04mm-1.60mm
- Application: For High Thermal Solderable High Applications
- Color: Could Be Customized
- Thermal Grade: 155
- Enamel Thickness: U2
- Diameter: 0.04mm-1.60mm
- Highlight: **1.6mm Enamelled Round Copper Wire, Enamelled Round Copper Wire Heat Resistant, 1mm enamelled copper wire UL**



for more products please visit us on enamel-wire.com

Product Description

0.04mm-1.60mm UEWF U2 High Thermal Polyurathane enamelled wire Thermal class 155

Compared with the UEW series, the UEF1 has the following features:

High heat resistance: UEF1 enameled wire has a heat resistance class F, with a heat resistance temperature index of up to 155°C. This characteristic enables UEF1 enameled wire to withstand the high temperatures generated by electrical equipment such as motors and transformers during operation, which ensures the stability and reliability of the equipment.

Wide application: UEF1 enameled wire is widely used in various motors, electrical appliances and household appliances, etc. Especially in recent years, the electric power industry has realized a sustained and rapid growth, and the rapid development of household appliances has brought a broader space for the application of UEF1 enameled wire.

Better insulation performance. The thickness of the insulation layer of UEF1 can reach 0.03-0.3mm, and it has excellent withstand voltage characteristics in high-voltage environments. This makes it ideal for transformer and motor applications that require a higher level of insulation.

During the manufacturing process of motor windings, UEF1 can withstand greater mechanical stress without damaging the insulation layer.

excellent thermal stability, UEF1 heat-resistant temperature up to 155° C or more, than the UEW is more suitable for the working environment of higher temperature occasions, such as high-power motor stator windings.





JIS---2種													Unit mm
Diameter of Conductor	Conductor Control Benchmarks		OD Control Benchmarks		Specification Boundaries		Conductor Resistance 20 (Ω/KM)	Insulation breakdown voltage (v)	Min Elongation (%)		Max. Springiness (°)	Resistance to abrasion	Unit mm
	Lower Limit	Upper Limit	Lower Limit	Max. Allowable	Min. Increase in Diameter (mm)	Max. Finished overall Diameter (mm)			J	A			
0.04±0.002	0.039	0.041	0.047	0.050	0.006	0.056	15670	200	7	11	--	---	
0.05±0.003	0.049	0.051	0.059	0.062	0.008	0.069	10240	950	11	04	--	---	
0.06±0.003	0.059	0.061	0.069	0.072	0.008	0.081	6966	950	11	05	--	---	
0.07±0.003	0.069	0.071	0.079	0.082	0.008	0.091	4990	950	11	07	--	---	
0.08±0.003	0.079	0.081	0.091	0.095	0.010	0.103	3778	1100	11	07	--	---	
0.09±0.003	0.089	0.091	0.102	0.106	0.010	0.113	2959	1100	11	08	--	---	

0.10±0.003	0.099	0.101	0.112	0.111	0.120	0.010	0.125	2381	1100	159	19	--	---
0.11±0.003	0.109	0.111	0.122	0.126	0.130	0.010	0.135	1957	1100	159	19	--	---
0.12±0.003	0.119	0.121	0.134	0.138	0.142	0.012	0.147	1636	1300	150	20	--	---
0.13±0.003	0.129	0.131	0.144	0.148	0.152	0.012	0.157	1389	1300	150	20	--	---
0.14±0.003	0.139	0.141	0.154	0.158	0.162	0.012	0.167	1193	1300	151	20	--	---
0.15±0.003	0.149	0.151	0.164	0.168	0.172	0.012	0.177	1037	1300	151	20	--	---
0.16±0.003	0.159	0.161	0.176	0.180	0.184	0.014	0.189	908.8	1300	152	20	--	---
0.17±0.003	0.169	0.171	0.186	0.190	0.194	0.014	0.199	803.2	1300	153	20	--	---
0.18±0.003	0.179	0.181	0.198	0.202	0.206	0.016	0.211	715.0	1600	153	20	--	---
0.19±0.003	0.189	0.191	0.208	0.212	0.216	0.016	0.221	640.6	1600	153	20	--	---
0.20±0.003	0.198	0.201	0.218	0.222	0.226	0.016	0.231	577.2	1600	154	20	--	---
0.21±0.003	0.208	0.212	0.228	0.232	0.236	0.016	0.241	522.8	1600	154	20	--	---
0.22±0.004	0.218	0.222	0.238	0.242	0.246	0.016	0.252	480.1	1600	154	20	--	---
0.23±0.004	0.228	0.232	0.250	0.254	0.258	0.018	0.264	438.6	1600	154	20	--	---
0.24±0.004	0.238	0.242	0.260	0.264	0.268	0.018	0.274	402.2	1600	154	20	--	---
0.25±0.004	0.248	0.252	0.270	0.274	0.278	0.018	0.284	370.2	1600	155	20	66	---
0.26±0.004	0.258	0.262	0.280	0.284	0.288	0.018	0.294	341.8	1600	155	20	66	224034
0.27±0.004	0.268	0.272	0.290	0.294	0.298	0.018	0.304	316.6	1600	156	20	61	224034
0.28±0.004	0.278	0.282	0.300	0.304	0.308	0.018	0.314	294.1	1600	156	20	61	224034

1.20±0.012	1.195	1.203	1.242	1.258	0.036	1.264	15.55	3050	252	3	54	545619
1.30±0.012	1.295	1.305	1.344	1.358	0.040	1.364	13.23	3400	253	3	50	652220
1.40±0.012	1.395	1.405	1.444	1.458	0.040	1.464	11.39	3400	253	3	46	652220
1.50±0.012	1.495	1.505	1.546	1.560	0.040	1.568	9.91	3400	253	3	46	652220
1.60±0.012	1.595	1.605	1.646	1.660	0.040	1.668	8.71	3400	253	3	42	652220



Pacific Electric Wire & Cable (Shenzhen) Co., Ltd.



13265485132



sales09@pewsc.com



enamel-wire.com

No.9 Jin Long 4 Road Bao long Industrail Estate Longgang,Shenzhen, China